



KARAKOYUNLU  
G R O U P

## High-Density Polyethylene Specification

Mark - T60-475-119

<b>Melt flow rate, (2.16 kg) , g/10min</b>	4 -5,6
<b>Density, kg/m<sup>3</sup></b>	959-963
<b>Tensile yield strength, Mpa</b>	28
<b>Notched izod under load, J/m</b>	55
<b>Flexural modulus ( 1 mm/min ), Mpa</b>	1250
<b>Heat resisitance on Vicka</b>	120 °C